



FINE GROUT


PRODUCT

FINE GROUT with Grout Additive

DESCRIPTION

PMP Fine Grout with Grout Additive is a preblended grout for filling masonry cavities and door frames, concrete patching and grouting. It is a blend of washed sand, Type II cement 2 1/2 : 1 and PMP Grout Additive, which gives the mortar its fluid properties at a reduced water to cement ratio. It also improves the bond and shrinkage compensation.





APPLICATIONS

Add PMP Fine Grout with Grout Additive to clean, potable water and thoroughly mix to the desired slump. Do not over water as this will have a negative effect on strength. Flowing properties are best within the first 30 - 40 minutes after mixing.

LIMITATIONS

- Do not apply when temperature is below or may fall below40°F prior to curing.
- Do not use with other admixtures unless approved in writing by E-Z Mix, Inc.

WARRANTY

The technical information and usage statement are based on our best knowledge. The content of this specification sheet is presented for information purposes only and do not constitute responsibility for their use. The manufacturer will replace only that material which is proven defective due to quality of the components of the manufacturing process.

CAUTION

Prolonged exposure to dust may cause delayed lung disease. Eliminate exposure to dust. Use NIOSH approved mask for silica dust. Freshly mixed material may cause skin irritation. Avoid direct contact when possible and wash exposed skin areas promptly with water and get prompt medical attention. See Safety Data Sheet.

USES

Grout for:

- Concrete Block
- Cavity Walls
- Around window and door frames

ADVANTAGES

- Fluid at low water ratio
- Minimum to no shrinkage
- Superior bonding properties
- Cohesive at high fluidity

PACKAGING

PMP Fine Grout with Grout Additive is packaged in multi-wall, 94 lb. paper bags and 3000 lb. bulk bags. Store in a cool dry area.

TECHNICAL DATA

PMP Fine Grout with Grout Additive meets ASTM C476 specifications. The product is L.A. City Approved (RR#24968). PMP Fine Grout with Grout Additive will meet 3000 psi compressive strength when placed at an 8"- 11" slump and tested in accordance with ASTM Standards. Recommended water for an 8" - 11" slump is approximately 8 - 9 quarts per 94 lb. bag.

COVERAGE

One 94 lb. bag will yield approximately 0.85 - 0.90 cubic feet.

For technical support contact:

www.ezmixinc.com jjara@ezmixinc.com

Corporate Office: 11374 Tuxford St. Sun Valley, CA 91352 (818) 767-8576 **Sun Valley Plant:** 11450 Tuxford St. Sun Valley, CA 91352 (818) 768-0568 **Rialto Plant:** 3355 Industrial Drive. Rialto, CA 92316 (909) 874-7686



WARNING: This product can expose you to chemicals including Chromium (hexavalent compounds), which are known to the state of California to cause cancer and birth defects or other reproductive harm. For more information go to **www.P65Warnings.ca.gov**.